CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST RESULTS OF GRADATION FOR WMM

Lab ID	:	**CP-RW-2017-03-14-01** **Date: 15-03-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Drilling of Borewells and providing pipe line to existing Borewell at Yelahanka old town and surrounding area Ward No-01.
Agency	:	Technical Manager (West) KRIDL, BBMP, Bangalore.
Customer Reference	:	BBMP/EE(YNK.D)/WO/122/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	14-03-17
Sample ID No	:	2017-03-14-01-01
Type of Mix	:	WMM (Wet Mix Macadam)
Date of test	:	14-03-17
Oven Dry Weight	:	11800 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0	100	100
45	505	505	4.3	95.7	95-100
22.4	2959	3464	29.4	70.6	60-80
11.2	1471	4935	41.8	58.2	40-60
4.75	2558	7493	63.5	36.5	25-40
2.36	1602	9095	77.1	22.9	15-30
0.6	610	9705	82.2	17.8	8-22
0.075	1690	11395	96.6	3.4	0-5

Note:-

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared By:
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-RW-2017-03-14-01** **Date: 15-03-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Drilling of Borewells and providing pipe line to existing Borewell at Yelahanka old town and surrounding area Ward No-01.
Agency	:	Technical Manager (West) KRIDL, BBMP, Bangalore.
Customer Reference	:	BBMP/EE(YNK.D)/WO/122/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	14-03-17
Sample ID No	:	2017-03-14-01-01
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	14-03-17

Result:

Index	Percentage of Flakiness and Elongation Index	Secified limits as per MORTH specification table 400-12
Flakiness Index	13.5%	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	10.2%	
Combined Flakiness and Elongation Index for WMM	23.7%	

Note:-
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Prepared By:
Harshitha

AEE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF AGGEGRATE IMPACT VALUE
IS: 2386 Part IV

Lab ID	:	**CP-RW-2017-03-14-01** **Date: 15-03-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Drilling of Borewells and providing pipe line to existing Borewell at Yelahanka old town and surrounding area Ward No-01.
Agency	:	Technical Manager (West) KRIDL, BBMP, Bangalore.
Customer Reference	:	BBMP/EE(YNK.D)/WO/122/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	14-03-17
Sample ID No	:	2017-03-14-01-01
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	14-03-17

Sl.No	Particulars of observations	Index	TEST 1	TEST 2
1	Total weight of the surface dry sample sample (passing 12.5 mm and retained on 10mm sieve)	A	305.0	305.0
2	Weight of fraction passing 2.36mm sieve After giving 15 blows	B	73.5	73.9
3	weight of fraction retained 2.36mm sieve After giving 15 blows	C	231.0	230.3
4	Total weight of (B+C) is less than the initial weight (Weight A) by more than one gram the result shall be discarded and a fresh test made.	A-(B+C)	0.5	0.8
5	Aggregate impact value	(B/A)*100	24.1	24.2
6	Aggregate impact value (Mean of two tests)	Pecentage	24.2	

Note:-
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared By:
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AEE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |